



## Aluminum Hardeners

### Aluminum Gallium

Alloy	Composition Limits Maximum unless shown as a range				Aluminum Association Color Coding	Form
7% Ga	Ga	6.8 – 7.2	Si	0.05 max	N/A	Waffle Ingot
			Others Each	0.03 max		
			Fe	0.05 max		
			Others Total	0.10 max		